

PRODUCT DATA

MICOROX® 287 PRIMER

MICOROX® 287 PRIMER is a multipurpose, 40% solids primer that allows the application of other MICOROX® products, including resurfacers, liners, and coatings to old or green concrete. MICOROX® 287 PRIMER is applied to eliminate the conventional 28 day cure time by bonding to the fresh concrete surface and providing a chemical bond to the top coat. 287 PRIMER is moisture tolerant, has no odor and zero voc. It will typically reduce moisture transmission by better than 50% with one application.

PRODUCT DESCRIPTION:

MICOROX® 287 PRIMER is a three component, water reducible epoxy primer and sealer for use on green or damp concrete.

APPLICATIONS:

MICOROX® 287 PRIMER is designed for use with *green* concrete. The major advantage of using this primer is that it does not inhibit the adhesion of subsequently applied toppings. The new concrete cures completely while the overlay remains securely locked to it without the cracking, blistering or disbonding problems associated with topping *green* concrete. It also provides excellent adhesion to existing concrete.

USAGE:

- Immediate overlaying of new concrete surfaces.
- Primer for new or old concrete floors.
- A substitute for concrete curing compounds.
- To bond coatings to new concrete.
- To strengthen existing concrete.
- Over new cementitious grouts or caps used to pitch grade or fill existing surfaces.

PHYSICAL/CHEMICAL CHARACTERISTICS

Thickness: 6.4 mils wft (wet film thickness)

2.5 mils dft (dry film thickness)

Viscosity: . . . 35 cps. at 25° C/77° F

Weight Per Gallon: 8.75 lbs. per mixed gallon

Flashpoint: Closed cup:100°C/212° F minimum

Cure Rate: Allow . . 4 hours for tack free (at 25° C/77° F) 16 hours hard and dry Service Time: 6-8 hours

FEATURES:

- Adheres to damp concrete or masonry.
- Eliminates concrete dust.
- Eliminates the 28 concrete cure time.
- Fast curing.
- Prevents shrinkage cracks.
- No odor.
- Reduces downtimes and construction time.
- Improves concrete. strengths
- Roller, brush or spray application.

•

PACKAGING:

Available in 1½ and 3 gallon units.

	1½ gallon unit	4.2 gallon unit
Part A:	0.357 gal resin	1.0 gallon resin
Part B:	0.437 gal hardener	1.2 gallons hardener
Part C:	0.75 gallon water	2.0 gallon water

PREPARATION:

NEW CONCRETE: Use standard Portland cement (type 1) or high early strength (type 3) concrete without additives. hardeners, curing agents or sealers.

Surface must be set so it can be walked on (usually overnight) and must be free of surface dirt, oil spills, etc.

EXISTING CONCRETE:. Clean and prepare the concrete by mechanical means and /or acid-etch until all foreign matter has been removed. A rough surface is desired to provide an effective bonding profile. Sweep out, vacuum or absorb any standing water. A damp surface is acceptable however standing water will prevent penetration of the material.

APPLICATION:

Mix the MICOROX® 287 Primer. 287 PRIMER is provided in proportioned kits containing resin and hardener. The entire contents of the resin container is emptied into the hardener container and mixed with a drill for 2-3 minutes. After resin and hardener are combined, clean water is added slowly with mixing until the application viscosity is achieved. (3 quarts of water for the 1.5 gallon kit and 2.0 gallons for the 4.2 gallon kit.) No induction is required and the primer may be used immediately.

Pour the 287 onto the surface in a ribbon about 8 to 10 inches wide along the starting edge of the wall. Roller, brush or squeegee the 287 out over the surface to a thin coat of about 6.4 mils wet film thickness.

When overlaying with Micor Floor Resurfacers, Linings or Coatings allow the 1287 to cure to a tack

free finish. Generally 6 hours at 77° F or longer at lower temperatures.

TEMPERATURE LIMITATIONS:

During the installation and cure, maintain surface temperatures between 60° F and 80° F. Lower temperatures will affect cure time. Consult with Micor for details.

WORKING LIFE:

Two hour at 77° F.

PRECAUTIONS:

Read container labels and Material Safety Data Sheet before using all products. Contact with liquids Part A and Part B can cause irritation. Wear protective clothing. Cover hands with protective cream and/or gloves. Wear chemical splash goggles. Use only with adequate ventilation. Never recap a container of mixed material as the continuing reaction may cause an explosion.

COMPLEMENTARY DATA:

Our full service lab and technical engineers are available to assist you. For complete information on MICOROX® systems, contact your local MICOROX® Dealer or our factory at 800-284-4308.

LIMITED WARRANTY: Micor Company Inc. warrants to the original purchaser of its products that they are in conformance to the formulation standards of Micor Company, Inc. and that such products are free from manufacturing defects. Original purchaser's only remedy is replacement of the product. Micor does not warrant or guarantee the workmanship performed by any person or company installing its products. In no event shall Micor be liable for any incidental or consequential damages. This warranty is expressly given in lieu of all other warranties express or implied, including the warranties of merchantability and fitness for use and all other obligations or liabilities on Micor's part. Micor neither assumes nor authorizes any person or persons to assume for us any other liability in connection with the sale of Micor products. This warranty shall not apply to any of Micor's products which have been subject to alteration, abuse or misuse. Micor makes no warranty whatsoever in respect to parts, materials or accessories not supplied by Micor Co. which are used in connection with its products. The term "original purchaser" in this warranty applies to that person, company or corporation to which Micor Company Inc. sold its product or products. The original purchaser accepts these terms and conditions and hereby expressly waives any claim to additional

CAUTION: Always keep out of the reach of children.